

ICC-ES Evaluation Report

ESR-3753

Reissued August 2026

This report remains under an active [continuous compliance program](#) through the end of August 2027

ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.

Copyright © 2026 ICC Evaluation Service, LLC. All rights reserved.

DIVISION: 07 00 00— THERMAL AND MOISTURE PROTECTION Section: 07 21 00— Thermal Insulation	REPORT HOLDER: BRINC BUILDING PRODUCTS, INC.	EVALUATION SUBJECT: THERMALBUCK™	
--	---	---	---

1.0 EVALUATION SCOPE

Compliance with the following codes:

- 2018, 2015, 2012, and 2009 [International Building Code® \(IBC\)](#)
- 2018, 2015, 2012, and 2009 [International Residential Code® \(IRC\)](#)
- 2018, 2015, 2012 and 2009 [International Energy Conservation Code® \(IECC\)](#)

Properties evaluated:

- Surface-burning characteristics
- Thermal resistance (R-values)
- Physical properties

2.0 USES

2.1 ThermalBuck™:

ThermalBuck™ is used as a nonstructural thermal insulation element in buildings of Type V construction when installed in accordance with this report. The insulation is for use around the framed window and door openings of exterior walls.

3.0 DESCRIPTION

3.1 General:

ThermalBuck™ consists of a Type XIV, EPS (expanded polystyrene) thermal insulation profile, factory-applied Polyurethane/Polyurea coating having a 40 mil [0.040 inch (1.02 mm)] - nominal thickness.

ThermalBuck™ has an L-shaped cross-sectional profile and is available in varying lengths. The ThermalBuck™ EPS material complies with ASTM C578 as a Type XIV material, has a maximum thickness of 4 inches (102 mm), a nominal density of 2.4 pcf (32 kg/m³), a flame-spread index (FSI) not exceeding 25 and a smoke-developed index (SDI) not exceeding 450 when tested in accordance with ASTM E84. See [Table 1](#) for thermal resistance (R-value) of ThermalBuck™. See [Table 2](#) for various sizes of the ThermalBuck™ profiles.

4.0 DESIGN AND INSTALLATION

4.1 General:

Installation of ThermalBuck™ must comply with this report and the manufacturer's published installation instructions. The manufacturer's published installation instructions must be available at all times on the jobsite during installation.

ThermalBuck™ is installed around the perimeter of window and door openings of exterior walls. ThermalBuck™ is field-cut to fit the openings. Sealant is applied to the ThermalBuck™ surfaces in contact with the wall opening. Where ThermalBuck™ lengths meet at corners of openings, each ThermalBuck™ end is cut and mitered in a manner such that when the ends are joined, they make contact over the perimeter of both cut edges and the EPS core is not exposed, with only the Polyurethane/Polyurea coating visible. Sealant is added to the mitered ends and then butted together. ThermalBuck™ is then fastened to the wall opening framing with 2-inch (51 mm)-long galvanized roofing nails. The nails are driven through the ThermalBuck™ and into the face of the: lintel, header, trimmer studs and sill framing members that are perpendicular to the length of the exterior wall.

The interior of the building must be separated from the ThermalBuck™ with a thermal barrier as required in IBC Section 2603.4, or IRC Section R316.4, as applicable. Protection against condensation must be provided in accordance with 2018 IBC Section 1402.2 (2015, 2012 and 2009 IBC Section 1403.2). A vapor retarder must be provided in accordance with 2018, 2015 and 2012 IRC Section R702.7 or 2009 IRC Section R601.3. A water-resistive barrier in compliance with 2018 IBC Section 1403.2 (2015, 2012 or 2009 IBC Section 1404.2) and IRC Section R703.2, is required and, when applied over wood-based sheathing, must comply with IBC Section 2510.6 or 2018 and 2015 IRC Section 703.7.3 or 2012 and 2009 IRC Section R703.6.3. Flashing of windows and doors, incorporating the water-resistive barrier is required in accordance with 2018 IBC Section 1404.4 (2015, 2012 and 2009 IBC Section 1405.4) or IRC Section R703.2. The attachment of wall coverings over the ThermalBuck must provide a minimum 1-inch (25.4 mm) penetration of the wall covering fasteners into wood framing members. Exterior wall assembly, exterior finish or a wall covering over the ThermalBuck™ must be structurally adequate to resist the required design wind pressures acting on the wall.

ThermalBuck™ must not be used as a nailing base for exterior siding materials. All fastening must penetrate through the ThermalBuck™ and into the wall framing or into structural sheathing, as required by the siding manufacturer's published installation instructions, or in accordance with the applicable code.

5.0 CONDITIONS OF USE:

The ThermalBuck™ product described in this report comply with, or is a suitable alternative to what is specified in, those codes listed in Section 1.0 of this report, subject to the following conditions:

- 5.1 The ThermalBuck™ must be installed in accordance with this report, the manufacturer's published installation instructions and the applicable code. In the event of a conflict between the installation instructions and this report, this report governs.
- 5.2 The ThermalBuck™ must be separated from the building interior with a thermal barrier complying with the applicable code, such as minimum ½-inch-thick (12.7 mm) gypsum wallboard installed in accordance with the applicable code.
- 5.3 ThermalBuck™ must be protected by a water-resistive barrier complying with 2018 IBC Section 1403.2 (2015, 2012 and 2009 IBC Section 1404.2) or IRC Section R703.2, and flashing in accordance with 2018 IBC Section 1404.4 (2015, 2012 and 2009 IBC Section 1405.4) or IRC Section R703.4.
- 5.4 Jobsite certification and labeling of the insulation must comply with 2018 and 2015 IRC Section N1101.10.1, 2012 IRC Section N1101.12.1, 2009 IRC Section N1101.4 and IECC Section 303.1.1, as applicable.
- 5.5 Use of ThermalBuck™ as a flashing material is outside the scope of this report.

6.0 EVIDENCE SUBMITTED

- 6.1 Data in accordance with the [ICC-ES Acceptance Criteria for Foam Plastic Insulation \(AC12\)](#), dated June 2015 (editorially revised October 2017).
- 6.2 Test reports in accordance with ASTM E84.

7.0 IDENTIFICATION

7.1 ThermalBuck™ must be packaged in bundles that are labeled with the manufacturer's name (BRINC Building Products, Inc.) and address; the date of manufacture; the product name (ThermalBuck™); the density (2.4 pcf); the thermal-resistance *R*-value (when applicable); and the evaluation report number (ESR-3753).

7.2 The report holder's contact information is the following:

BRINC BUILDING PRODUCTS, INC.
3089 BROOKVILLE STREET
NEW BETHLEHEM, PENNSYLVANIA 16242
(814) 275-5002
<https://www.brincbp.com>

TABLE 1—MINIMUM *R*-VALUE (°F·ft²·h/Btu) AT 75°F MEAN TEMPERATURE

PROPERTY	TYPE XIV
Density, min., lb/ft ³ (kg/m ³)	2.40 (38.4)
Thermal resistance value, Per inch of thickness at 75°F·ft ² ·h/Btu (°K·m ² /W)	4.20 (0.74)

For SI: 1 lb/ft³ = 16.018 kg/m³, 1°F·ft²·h/Btu = 0.176°K·m²/W, 1inch = 25.4 mm.

TABLE 2—THERMALBUCK™ CROSS-SECTIONAL DIMENSIONS (inches)

MODEL	DIMENSION									
	A	B	C	C	C	D	E	E	E	F
W0505	3.0	0.5	2.5	4.0	6.0	2.5	2.0	3.5	5.5	0.5
W0510	3.5	0.5	2.5	4.0	6.0	2.5	2.0	3.5	5.5	1.0
W0515	4.0	0.5	2.5	4.0	6.0	2.5	2.0	3.5	5.5	1.5
W0520	4.5	0.5	2.5	4.0	6.0	2.5	2.0	3.5	5.5	2.0
W0525	5.0	0.5	2.5	4.0	6.0	2.5	2.0	3.5	5.5	2.5
W0530	5.5	0.5	2.5	4.0	6.0	2.5	2.0	3.5	5.5	3.0
W0535	6.0	0.5	2.5	4.0	6.0	2.5	2.0	3.5	5.5	3.5
W0540	6.5	0.5	2.5	4.0	6.0	2.5	2.0	3.5	5.5	4.0

For SI: 1inch = 25.4 mm.




FIGURE 1—THERMALBUCK™ CROSS-SECTIONAL VIEW